



EMSL Analytical, Inc.

200 Route 130 North Cinnaminson, NJ 08077
Phone/Fax: (800) 220-3675 / (856) 786-5974
<http://www.EMSL.com> / cinnasblab@EMSL.com

EMSL Order ID: 042503300
Customer ID: WSPL75
Customer PO:
Project ID:

Attn: Andrew Shust
WSP
2000 Lenox Drive
3rd Floor
Lawrenceville, NJ 08648
Proj: US0043268.2150

Phone: (609) 512-3451
Fax:
Collected: 2/23/2025
Received: 2/24/2025
Analyzed: 2/25/2025

Summary Test Report for Asbestos Analysis of Bulk Material

Client Sample ID: D-1 **Lab Sample ID:** 042503300-0001

Sample Description: Parking Lot Grass Area/White Skim Coating

TEST	Analyzed Date	Color	Non-Asbestos		Asbestos	Comment
			Fibrous	Non-Fibrous		
PLM	2/24/2025	White	15.0%	85.0%	None Detected	
TEM Grav. Reduction	2/25/2025	White	0.0%	100.0%	None Detected	

Client Sample ID: D-2 **Lab Sample ID:** 042503300-0002

Sample Description: Parking Lot Grass Area/White Skim Coating

TEST	Analyzed Date	Color	Non-Asbestos		Asbestos	Comment
			Fibrous	Non-Fibrous		
PLM	2/24/2025	White	0.0%	100.0%	None Detected	
TEM Grav. Reduction	2/25/2025	White	0.0%	100.0%	None Detected	

Client Sample ID: D-3 **Lab Sample ID:** 042503300-0003

Sample Description: Parking Lot Grass Area/White Skim Coating

TEST	Analyzed Date	Color	Non-Asbestos		Asbestos	Comment
			Fibrous	Non-Fibrous		
PLM	2/24/2025	White	0.0%	100.0%	None Detected	
TEM Grav. Reduction	2/25/2025	White	0.0%	100.0%	<0.70% Anthophyllite	



EMSL Analytical, Inc.

200 Route 130 North Cinnaminson, NJ 08077
Phone/Fax: (800) 220-3675 / (856) 786-5974
<http://www.EMSL.com> / cinnasblab@EMSL.com

EMSL Order ID: 042503300
Customer ID: WSPL75
Customer PO:
Project ID:

Summary Test Report for Asbestos Analysis of Bulk Material

Analyst(s):

Brett Polumbo PLM (1)
Gregory Barry TEM Grav. Reduction (3)
Kiara Stefanik PLM (2)

Reviewed and approved by:

Samantha Rundstrom, Laboratory Manager
or Other Approved Signatory

EMSL maintains liability limited to cost of analysis. Interpretation and use of test results are the responsibility of the client. This is a summary report; official reports are available on LabConnect or upon request and relates only to the samples reported above, and may not be reproduced, except in full, without written approval by EMSL. EMSL bears no responsibility for sample collection activities or analytical method limitations. The report reflects the samples as received. Results are generated from the field sampling data (sampling volumes and areas, locations, etc.) provided by the client on the Chain of Custody. Samples are within quality control criteria and met method specifications unless otherwise noted. The above analyses were performed in general compliance with Appendix E to Subpart E of 40 CFR (previously EPA 600/M4-82-020 "Interim Method") but augmented with procedures outlined in the 1993 ("final") version of the method. This report must not be used by the client to claim product certification, approval, or endorsement by NVLAP, NIST or any agency of the federal government. Non-friable organically bound materials present a problem matrix and therefore EMSL recommends gravimetric reduction prior to analysis. Unless requested by the client, building materials manufactured with multiple layers (i.e. linoleum, wallboard, etc.) are reported as a single sample. Estimation of uncertainty is available on request.

Samples analyzed by EMSL Analytical, Inc. Cinnaminson, NJ NVLAP Lab Code 101048-0, AIHA LAP, LLC-IHLAP Lab 100194, PA ID# 68-00367, LA #04127

Report amended: 02/26/2025 07:30:15 Replaces amended report from: 02/25/2025 13:29:21 Reason Code: Client-Other (see report comment)